

Address: Road 8.Yanshan Industrial Estate Shangrao City, 334500, Jiangxi Prov.CHINA

Tel: +86-18024335478 E-mail: aaron@dgork.com

MATERIALS TEST REPORT

NBR60 BLACK FDA (N6001F) COMPOUND

ASTM D2000 M2BG 610 A14 B14 EO14 EO34 EA14 F17

Press Cure Post Cure				
Sheet : 5min 170℃	Sheet : 1 hrs 120°C Button : 1 hrs 120°C			
Button : 10 min 170℃				
ORIGINAL PROPERTIES	SPECIFICATION	TEST RESULT	ASTM TEST METHOD	
HARDNESS SHORE A	60°±5	60	D2240	
TENSILE STRENGTH, MPA, MIN	≥10	10.75	D412	
ULTIMATE ELONGATION, %, MIN	≥300	327.49	D412	
SPECIFIC GRAVITY (g/cm3)		1.23	D297	
HEAT RESISTANCE 70 H . AT 100°C (A14)			D573	
CHANGE IN HARDNESS, POINTS	+/-15	8		
CHANGE IN TENSILES STRENGTH, %	+/-30	-3.72		
CHANGE IN ULTIMATE ELONGATION,MAX %	-50	-32.69		
COMPRESSION SET, MAX, 22H AT 100°C (B14)	≤25	10.39	D395	
FLUID RESISTANCE NO.1 OIL, 70H AT 100°C (EO14)			D471	
CHANGE IN HARDNESS, POINTS	-5~+10	10		
CHANGE IN TENSILES STRENGTH, MAX %	-25	30.05		
CHANGE IN ULTIMATE ELONGATION,MAX %	-45	-18.30		
CHANGE IN VOLUME %	-10~+5	-9.65		
FLUID RESISTANCE NO.3 OIL, 70H AT 100°C (EO34)			D471	
CHANGE IN HARDNESS, POINTS	-10~+5	5		
CHANGE IN TENSILES STRENGTH, MAX %	-45	0.84		
CHANGE IN ULTIMATE ELONGATION,MAX %	-45	-16.77		
CHANGE IN VOLUME %	0~+25	2.29		
WATER RESISTANCE:100°C,70H(EA14)			D471	
CHANGE IN HARDNESS, POINTS	±10	+2		
CHANGE IN VOLUME %	±15	-2.92		
LOW-TEMPERATURE BRITTLENESS NONBRITTLE				
AFTER 3MIN AT -40°C (F17)	NONBRITTLE	PASS	D2137	

Remark:

- 1. The data are based on testing slabs I buttons and are for reference purpose only..
- 2. Our compound can meet above -mentioned ASTM 2000 Spec.
- 3. This information is, to the best of our knowledge, accurate reliable to the date indicated.
- 4. The above mentioned data have been obtained by tests we consider as reliable, We don't assure that
- the same results can be obtained other laboratories, using different conditions by the preparation and -evaluation of the samples.

Approved By:	Wendy Wen	Audit By:	Yunli Tu	Test By:	Jianjun Zhu
--------------	-----------	-----------	----------	----------	-------------