

# SHANGRAO RUICHEN SEALING CO.,LTD DONGGUAN RUICHEN SEALING CO.,LTD

Address: Road 8.Yanshan Industrial Estate, Shangrao City, 334500, Jiangxi Prov., CHINA

Tel: +86-18024335478 E-mail: aaron@dgork.com

### **MATERIALS TEST REPORT**

## N7001 (NBR 70 BLACK) COMPOUND

# ASTM D2000 M2BG 714 A14 B14 EO14 EO34 EA14 F17

| Press Cure                                    |                     | Post Cure Sheet : 1 hrs 120°C |                  |  |  |
|---|---------------------|-------------------------------|------------------|--|--|
| Sheet : 5min 170°C                            |                     |                               |                  |  |  |
| Button : 10 min 170°C                         | Button: 1 hrs 120°C |                               |                  |  |  |
| ORIGINAL PROPERTIES                           | SPECIFICATION       | TEST RESULT                   | ASTM TEST METHOD |  |  |
| HARDNESS SHORE A                              | 70°±5               | 70                            | D2240            |  |  |
| TENSILE STRENGTH, MPA, MIN                    | ≥14                 | 16.47                         | D412             |  |  |
| ULTIMATE ELONGATION, %, MIN                   | ≥250                | 336.00                        | D412             |  |  |
| SPECIFIC GRAVITY (g/cm³)                      |                     | 1.23                          | D297             |  |  |
| HEAT RESISTANCE 70 H . AT 100℃ (A14)          |                     |                               | D573             |  |  |
| CHANGE IN HARDNESS, POINTS                    | +/- 5               | 3                             |                  |  |  |
| CHANGE IN TENSILES STRENGTH, %                | +/-15               | -8.65                         |                  |  |  |
| CHANGE IN ULTIMATE ELONGATION,MAX %           | -15                 | -13.15                        |                  |  |  |
| COMPRESSION SET, MAX, 22H AT 100℃ (B14 )      | ≤25                 | 12.66                         | D395             |  |  |
| FLUID RESISTANCE NO.1 OIL, 70H AT 100℃ (EO14) |                     |                               | D471             |  |  |
| CHANGE IN HARDNESS, POINTS                    | -5~+10              | 2                             |                  |  |  |
| CHANGE IN TENSILES STRENGTH, MAX %            | -25                 | 7.10                          |                  |  |  |
| CHANGE IN ULTIMATE ELONGATION,MAX %           | -45                 | -10.63                        |                  |  |  |
| CHANGE IN VOLUME %                            | -10~+5              | -2.89                         |                  |  |  |
| FLUID RESISTANCE NO.3 OIL, 70H AT 100℃ (EO34) |                     |                               | D471             |  |  |
| CHANGE IN HARDNESS, POINT                     | -10~+5              | -5                            |                  |  |  |
| CHANGE IN TENSILES STRENGTH, MAX %            | -45                 | -9.90                         |                  |  |  |
| CHANGE IN ULTIMATE ELONGATION,MAX %           | -45                 | -6.92                         |                  |  |  |
| CHANGE IN VOLUME %                            | 0~+25               | 9.31                          |                  |  |  |
| WATER RESISTANCE:100℃,70H (EA14)              |                     |                               | D471             |  |  |
| CHANGE IN HARDNESS, POINTS                    | ±10                 | +2                            |                  |  |  |
| CHANGE IN VOLUME %                            | ±15                 | -2.17                         |                  |  |  |
| LOW-TEMPERATURE BRITTLENESS NONBRITTLE        |                     |                               |                  |  |  |
| AFTER 3MIN AT -40°C (F17)                     | NONBRITTLE          | PASS                          | D2137            |  |  |

### Remark:

- 1. The data are based on testing slabs I buttons and are for reference purpose only..
- 2. Our compound can meet above -mentioned ASTM 2000 Spec.
- 3. This information is, to the best of our knowledge, accurate reliable to the date indicated.
- 4. The above mentioned data have been obtained by tests we consider as reliable, We don't assure that
- the same results can be obtained other laboratories, using different conditions by the preparation and

-evaluation of the samples.

| Approved By: | Franky Fang | Audit By: | Yunli Tu | Test By: | Jianjun Zhu |
|--------------|-------------|-----------|----------|----------|-------------|
|--------------|-------------|-----------|----------|----------|-------------|